

File No.: PM-ER18505-S-02-LF Dec. 2015 V201 version: A

TECHNICAL SPECIFICATION

Lithium-Thionyl Chloride Battery

Model: ER18505

Approved	Checked	Draft
Zhu yuan	Hu guohua	Gao kun

Customer signature
Company name:
Approved by:
Signature date:



Page 1 of 11



Established date: 15 Dec. 2015

Huizhou EVE Energy Co., Ltd.



Revision Record

Version	Reviser	Revise page	Established Date	Revise reason
0	Hu guohua	All	2010.4.24	Release
1	Nan fen	Page 3, 4, 7, 8, 9 and 10	2014.09.10	 Page 3, 3.3 remark add "(the actual measuredcut-off voltage)"; Page 3, 3.4 remark modify to "Operation under higher please consult EVE "; Page 4, "20±3°C" modify to "20±5°C"; Page 7, safety standard "UL1642 - Fourth Edition -2007" update to "UL1642- Fifth Edition - 2013"; Page 8, the 8 chapter Incoming inspection, add table 1 and table 2; Page 9, the 11 chapter transportation, update " the tests and Criteria requirements of UN Manual" to fifth modification; Page 10, add "12 modification of this specification" and "13 important notes"; Page 10, the 14 chapter add "Operation at temperature voltage reading at the beginning of pulses" content.
А	Gao kun		2015.12.15	Updating



1. Scope

The document applies to ER18505 (Li/SOCl₂) battery supplied by EVE Energy Co., Ltd. Specify quality, test method, performance, quality assurance and matters need attention etc..

2. Battery type

Lithium Thionyl Chloride

3. General characteristics

No.	ltem	Characteristic	Remarks
3.1	Туре	ER18505	Bobbin type battery
3.2	Nominal Voltage	3.6V	Tested with 36K Ω /0.1mA load at +20 $^\circ \! \mathbb{C}$
3.3	Nominal capacity	4.0Ah	At 1.2KΩ/3mA load, 2.0V cut off, +20°C (the actual measured capacity value will be changed by discharge current, temperature and cut-off voltage).
3.4	Operating temperature	-60℃~+85℃	Operation under higher temperature than ambient temperature may lead to reduced capacity and lower voltage reading at the beginning of pulses. If continuous high temperature over +40°C or low temperature down to -20°C usage conditions, please consult EVE.
3.5	Outside dimensions	Diameter Φ 18.7mm Max. Height H 50.5mm Max.	Please ref. to the production drawing
3.6	Nominal weight	About 28g	
3.7	Volume of battery	About 14cm ³	

4. Appearance and structure

4.1 Appearance

When checking the ER18505 cell appearance by eye, no scratch, swelling, deformation, corrosion, electrolyte leakage and other defects.





ER18505 is "bobbin design" cell, which cathode is cylindrical in shape.

Hermetic is ensured by a glass-to-metal sealing technology. (under a standard helium pressure, leakage rate $\leq 10^{-7}$ atm.cc/sec).

5. Typical electrical performances

ltem	Test condition	Initial Values*	Typical values after store for one year at $\leq 30^{\circ}C^{**}$	
5.1 Open Circuit Voltag	5.1 Open Circuit Voltage			
Room temperature	20±5 ℃	3.63~3.70V	3.63~3.73V	
Low temperature	-40±2℃	3.63~3.70V	3.62~3.72V	
High temperature	70±2 ℃	3.63~3.74V	3.64~3.74V	
5.2 Load voltage	5.2 Load voltage			
Room temperature	165Ω (20mA) discharge 2s	3.30V	3.20V	
5.3 Operation voltage	discharge with 1.2kΩ load(3mA)			
Room temperature	20±5 ℃	Min.: 3.5V	Min.: 3.4V	
Low temperature	-40±2℃	Min.: 3.1V	Min.: 3.0V	
High temperature	70±2 ℃	Min.: 3.5V Min.: 3.4V		
5.4 Service life				
Cut off voltage is 2.0V, 1.2KΩ/3mA load, Orientation: positive up-right				
Room temperature	20±5 ℃	Min.: 1200h	Min.: 1150h	
Room temperature	Discharge loading: 96Ω	Min.: 80h	Min.: 75h	
5.5 Electrolyte Leakage test	above 1-4 item's testing	No leakage		
5.6 Deformation	above 1-4 item's testing	The cell size don't exceed attached drawing's dimension.		



Note: *****: Test data within 1 month according to the date code on shrink tube.

******: Test data within $1 \sim 12$ months according to the data code on shrink tub.

6. Safety and environmental performance

6.1 Environmental test

6.1.1 Temperature cycling test

According to the UL* test requirement, the batteries are to be placed in a test chamber and subjected to the following cycles: raising the chamber temperature from $20\pm3^{\circ}$ C to $70\pm3^{\circ}$ C within 30min, and maintaining for 4h, then reducing the chamber temperature to $20\pm3^{\circ}$ C and maintaining for 2h, then reducing to $-40\pm3^{\circ}$ C and keep it for 4h, at last, raising to $20\pm3^{\circ}$ C within 30min. Repeating the sequence for a further 10 cycles.

Pass/Fail criteria: the samples shall not explode or catch fire. In addition, the samples shall no leakage.

6.1.2 Low pressure (Altitude Simulation) test

According to the UL* test requirement, sample batteries are to be stored for 6h at an absolute pressure of 11.6KPa(1.68psi) and a temperature of $20\pm3^{\circ}$ C (68±5°F)

Pass/Fail criteria: The batteries shall be no explosion or catch fire as a result of the altitude simulation test. In addition the samples shall be no vent or leakage.

6.1.3 Free fall test

According to the IEC** test requirement, each cell should be dropped 2 times from 1m height onto cement ground (total 6 times).

Pass/Fail criteria: The battery samples shall be no explosion or catch fire. In addition, the samples shall no vent or leakage.

6.1.4 Vibration test

According to the UL* test requirement, a battery vibration frequency is to be varied at the rate of 1 hertz per minute between 10 and 55 hertz, and return in not less than 90 or more than 100 minutes. The battery is to be tested in three mutually perpendicular directions

Pass/Fail criteria: The battery samples shall be no explosion or catch fire. In addition, the samples shall no vent or leakage.



Warning: The description of the following abuse tests is for demonstration purposes only. During handling and application of lithium batteries, abusive conditions must be avoided. Any application or test requiring performance beyond the limits given hereby must be approved by EVE.

6.2 Safety test

6.2.1 Heating test

According to the UL* test requirement, a battery is to be heated in a gravity convection or circulating air oven. The temperature of the oven is to be raised at a rate of $5\pm2^{\circ}$ C per minute to a temperature of $130\pm2^{\circ}$ C and remain for 10 minutes at that temperature before the test is discontinued.

Pass/Fail criteria: The battery samples shall be no explosion or catch fire.

6.2.2 Impact test

According to the UL* test requirement, a test sample cell was placed on a flat surface. A 5/8 in. (15.8 mm) diameter steel bar was placed across the center of the sample. The length of the bar should be at least as long as the width of the sample. A 20 pound (9.1 kg) weight was dropped from a height of 24 ± 1 in. (610 ± 25 mm) on to the sample.

Pass/Fail criteria: The samples shall not explode or catch fire.

6.2.3 Crush test

According to the UL* test requirement, a cell was crushed between two flat hard surfaces (i.e. steel). The crushing was continued until a force of 3000 pounds (13kN±0.78kN) was applied. The speed of the crush was documented for information purposes. Once the maximum pressure was obtained, it was released.

Pass/Fail criteria: The battery samples shall be no explosion or catch fire.

6.2.4 External Short-circuit test

According to the UL* test requirement, each test sample, in turn, was short-circuited by connecting the positive and negative terminals of the sample with a circuit load having a maximum resistance < 0.1 ohm. The sample was discharged until a fire or explosion was obtained, or until it had reached a completely discharged state of less than 0.2 volts and the cell case temperature had returned to +10°C (+18°F) of ambient temperature.

Pass/Fail criteria: The battery samples shall be no explosion or catch fire.



6.2.5 Abnormal charging test

According to the UL* test requirement, each test sample battery is to be subjected to a charging current of three times the current Ic, specified by the manufacturer by connecting it in opposition to a dc-power supply. The specified charging current is to be obtained by connecting a resistor of the specified size and rating in series with the battery.

The test charging time is to be calculated using the formula:

Tc=2.5*C/(3*lc)

In which

Tc—charge time, hour, Tc \geq 7Hour;

C——Nominal capacity, Ah;

Ic—Max. charging current, mA. ER18505 maximum charge current is 0.010A.

Pass/Fail criteria: The samples shall be no explosion or catch fire.

6.2.6 Forced-discharge test

According to the UL* test requirement, a completely discharged cell is to be force-discharged by connecting it in series with fully charged cells of the same kind. The number of fully charged cells to be connected in series with the discharged cell is to equal the maximum number less one of the cells to be covered for series use, the circuit load resistance less than 0.1 Ω . The sample is to discharge until a fire or explosion is obtained, or until it has reached a completely discharge state of less than 0.2V and battery case temperature has returned to $\pm 10^{\circ}C(+18^{\circ}F)$ of ambient temperature.

Pass/Fail criteria: The samples shall be no explosion or catch fire.

References to safety standards

*UL Underwriters Laboratories "Standard Lithium Battery"—UL1642—Fifth Edition—2012。 **IEC International Electro technical Commission International safety standards for lithium batteries "IEC 60086-4" –Third Edition – 2007

Note: This specification use the latest release version of the standard documents above as the criterion

7. Product mark

7.1 Battery's label specification

- ①type ② nominal voltage ③ positive and negative electrode mark
- (4) date code (5) safety warning



Date code will be marked on the sleeve of battery.

Method: MM YY XXX, "MM" stand for: month; "YY" stand for: year;

"XXX" stand for: Order serial number.

8. Incoming inspection

Before shipping, EVE will 100% check open circuit voltage of the battery (OCV) and the load voltage.

Also EVE will sampling tests the battery capacity, visual appearance and size.

As for the customer's incoming inspection, EVE recommended sampling according to GB2828.1-2003, GB2829-2002 standard.

No	Item	Technical request	Check level	AQL
1	Dimension	2-6	S-2	0.65
2	Appearance	2-8	II	1.0
3	Open circuit voltage	3-1	II	0.4

Table 1 Acceptability quality level

Table 2 Sampling amount

Lot size	sampling amount
≤3200	32
3200~10 000	50
>10 000	80

9. Storage

Lithium batteries should be stored in a cool, clean, dry environment, the recommended temperature is \leq +30°C, relative humidity \leq 60%, should avoid contact with corrosive materials, away from fire and heat.

10. Safety

10.1 We propose to use lithium cell process, need to comply with the following provisions:

- Before use, do not remove the battery from the original packaging.
- Do not scattered placed the battery together in order to avoid accidental short circuit.





- Do not heat the battery above 100 °C or incinerated.
- Do not recharge the battery.
- Do not weld or solder directly to battery, should use the battery with terminals or wires.
- Do not mix the new and used batteries or different brand battery.
- Do not disassembly or open battery
- Do not short circuit the battery or reversely contact the positive and negative terminals.

EVE Battery verified by Underwriters Laboratory as "engineers replace batteries."

10.2 Backups circuit design prevent charging battery

The following diagram shows by the Underwriters Laboratory recommended the protection of memory backup circuit reverse charging circuit, shown in Figure 10-1. If the resistance R is diode replaced by Figure 10-2 is also available. Set such a safety device in the circuit board is absolutely necessary, which includes a backup battery and power supply in parallel. Safety devices should be as close as possible the battery. Otherwise, do not intend to short circuit in the adjacent PCB or bad solder joints, may bypass the safety device, so that the power supply through the reverse (charging) current through the battery.



FIG. 10-1

FIG. 10-2

11. Transportation

ER18505 battery has been proven to meet the tests and Criteria requirements of UN Manual, Part III, subsection 38.3 (Document No.: ST/SG/AC.10/11/Rev 5-2011). According to U.N. "Recommendations on the Transport of Dangerous Goods Model Regulations" (Document No.: ST/SG/AC.10/1- Rev 16 (Vol. I) -2009), The ER18505 battery's lithium content is more than 1g, So ER18505 battery is restricted for transport of class 9.

ER18505



12. Modification of this specification

Modification must be carried out after the prior mutual agreement. All accident or issues caused by any events that are neither defined nor described in this specification, mutual discussion shall take place for the resolution.

13. Important notes

- 1) The batteries are warranted to conform to the description contained in this specification for a period of twelve [12] months from the ex-factory date without use (after 6 months storage, EVE recommend to active the battery, more details please consult EVE), any claim by customer (apparatus manufacturer or distributor) must be pointed out within such period. During that warranty period, if the batteries are proved to become defective under proper stored and handled, EVE will replace the batteries for free.
- Customers are responsible to confirm and assure the matching and reliability of batteries under actual application.
- 3) EVE shall not warrant or be responsible in any case where customers fail to carry out proper handing, operating, installation, testing and maintaining batteries, or don't follow the instruction, cautions, warnings, notes provided in this specification and other EVE's reasonable instructions or advises.
- 4) This product specification will be validated assuming that it is accepted when it is not returned within six months from the date of issue.

14. Remark of production duty

Customers must strictly operate according to specification and advises of EVE ENERGY CO., LTD. Operation at temperature different from ambient may lead to reduced capacity and lower voltage reading at the beginning of pulses. EVE will be exemption from liability if the batteries are improper used or abused and then cause fire, explosion, the human body or property damage.



15. Drawing (unit of size: mm)



ER18505