SUNNY BOOM CO., LTD HEAT CONDUCTIVE NON-SMIOOTH SILICONE RUBBER SHEET



SPECIFICATION				
測試項目 Property	SB-100T		單位 Unit	測試標準 Test Method
顏色 Color (Any Color)	Gray			Visual
厚度 Total Thickness	0.3~ 1.0		mm	ASTM D374
比重 Specific Gravity	1.7		(ASTM D792
熱容量 Heat Capacity	1.0		J/g-k	ASTM D351
硬度 Hardness	78±5		Shore	ASTM D2240
耐温度範圍 Continuous Use Temp	-40~ +210		°C	EN344
拉力 Tensile Strength	>197		Kgf/ cm ²	ASTM D-412
撕裂強度 Breaking Strength	>6.7		Kgf/ cm	ASTM D-1458
延伸率 Elongation, %45 to warp & Fill	5-11		%	ASTM D-412
楊氏係數 Young's Modulus -	Modulus	Rate	Psi	ASTM D575
	15	0.25/min		
耐電壓 Dielectric Breakdown Voltage	3.5~7		KV	ASTM D149
熱絕緣係數 Dielectric Constant	6.5		°C- in²/W	ASTM D150
體積阻抗 Volume Resistivity	10 ¹³		Ω.CM	ASTM D257
防火性 Flame Rating	V-0			U.L - 94
導熱係數 Thermal Conductivity	1.3		W/mk	ASTM D5470

Remark : The above test result is from testing laboratory report, for your reference only.







Notes :

SB-100T : Gray Fine Spray Heat Silicone Rubber Sheets, Combined with Fiber glass and low-modulus polymer Function : Insulation, Heat Sink

Standard Thickness : 0.3mm to 0.8mm

Application: RDRAMTM, CDROM, CPU, appliances, any application need to have heat sink, insulation Remark : The above test result is from testing laboratory report, for your reference only.

Remark : The above test result is from testing laboratory report, for your reference only.

HEAD OFFICE: No. 6, Lane 183. Chung Hsin Road, Shijr, Taipei Taiwan. Tel : + 886 2 26943486 Fax: +886 2 26943309